

Thickness MM	CRGO Grade	Assumed KG/DM3	Maximum Core Loss		Minimum Induction at 800 A / m T
			At 1.5T	At 1.7T	
0.23	23ZDKH90	7.65		0.9	1.88
0.23 -0.009	23ZH90			0.9	1.88
	23ZH95			0.95	1.88
	M-0H			1	1.88
	M-1	7.65	0.71	1.06	1.8
	M-2		0.75	1.12	1.8
	M-3		0.79	1.04	1.8
0.27 -0.0106	27ZDKH95	7.65		0.95	1.88
	27ZH95			0.95	1.88
	27ZH100			1	1.8
	M-0H			1.03	1.88
	M-1H	7.65		1.09	1.88
	M-3		0.83	1.21	1.8
	M-4		0.89	1.27	1.8
0.3 -0.0118	30ZH100			1	1.88
	M-0H			1.05	1.88
	M-1H			1.11	1.88
	M-2H	7.65		1.17	1.88
	M-3		0.85	1.23	1.8
	M-4		0.9	1.32	1.8
	M-5		0.97	1.39	1.8
	M-1H			1.16	1.88
	M-2H			1.16	1.88
	M-3H			1.28	1.88
	M-5		1.01	1.45	1.8
	M-6		1.11	1.57	1.8